

Standard Colors



Premium Colors

Premium colors require a nominal surcharge.



Natural Metal Finish

Acrylic-Coated Galvalume® is a coated sheet product that combines the corrosion resistance of Galvalume® steel sheet with a clear, organic resin applied to the top side and backside of Galvalume® substrate.




Acrylic-Coated Galvalume®




Metallic Colors

Metallic colors are premium finishes which require a nominal surcharge.



Print Pattern Finishes

Consult BMC for current print pattern pricing, availability, and lead times. Due to normal production variation, print pattern finishes may vary slightly between production runs.



BERRIDGE STOCK AVAILABILITY AND COLOR DETAILS

S - Stock Color N - Non-Stocking Color N/A - Not Available

Standard Colors	24 Gauge		22 Gauge*		0.032 Aluminum*		0.040 Aluminum*		SR	EM	SRI
	48"	42"	48"	42"	48"	42"	48"	42"			
Aged Bronze	S	S	S	N	N	N	N	N	0.31	0.85	31
Almond	S	S	S	N	N	N	N	N	0.65	0.86	77
Bristol Blue	S	S	N	N	N	N	N	N	0.33	0.85	33
Buckskin	S	S	S	N	N	N	N	N	0.43	0.83	46
Burgundy	S	S	N	N	N	N	N	N	0.32	0.84	32
Charcoal Grey	S	S	S	S	N	N	N	N	0.29	0.84	28
Cityscape	S	S	S	S	N	N	N	N	0.48	0.85	54
Colonial Red	S	S	N	N	N	N	N	N	0.35	0.83	35
Copper Brown	S	S	N	N	N	N	N	N	0.32	0.85	32
Dark Bronze	S	S	S	S	N	N	N	N	0.28	0.85	27
Deep Red	S	S	N	N	N	N	N	N	0.41	0.84	44
Evergreen	S	S	N	N	N	N	N	N	0.30	0.83	29
Forest Green	S	S	S	N	N	N	N	N	0.30	0.83	29
Hartford Green	S	S	N	N	N	N	N	N	0.27	0.83	25
Hemlock Green	S	S	N	N	N	N	N	N	0.31	0.84	31
Jet Black	S	S	N	N	N	N	N	N	0.04	0.88	-2
Matte Black	S	S	S	S	N	N	N	N	0.26	0.83	24
Medium Bronze	S	S	S	S	N	N	N	N	0.31	0.85	31
Parchment	S	S	S	N	N	N	N	N	0.60	0.85	71
Patina Green	S	S	N	N	N	N	N	N	0.34	0.85	35
Royal Blue	S	S	N	N	N	N	N	N	0.27	0.85	26
Shasta White	S	S	S	N	N	N	N	N	0.61	0.85	73
Sierra Tan	S	S	S	N	N	N	N	N	0.39	0.85	42
Teal Green	S	S	N	N	N	N	N	N	0.26	0.84	25
Terra-Cotta	S	S	N	N	N	N	N	N	0.36	0.84	38
Zinc Grey	S	S	S	S	N	N	N	N	0.39	0.85	42
Acrylic-Coated Galvalume®	S	S	S	S	N/A	N/A	N/A	N/A	0.67	0.20	59
Premium Colors*											
Award Blue	S	S	N	N	N	N	N	N	0.17	0.83	11
Natural White	S	S	N	N	N	N	N	N	0.71	0.85	86
Metallic Colors*											
Antique Copper-Cote	S	S	N	N	N	N	N	N	0.33	0.84	34
Champagne	S	S	N	N	N	N	N	N	0.40	0.85	43
Copper-Cote™	S	S	N	N	N	N	N	N	0.51	0.85	59
Lead-Cote™	S	S	N	N	N	N	N	N	0.36	0.86	38
Preweathered Galvalume®	S	S	N	N	N	N	N	N	0.40	0.85	43
Zinc-Cote™	S	S	N	N	N	N	N	N	0.53	0.83	59
Print Pattern Finishes**											
COR-TEN AZP® Raw	S	N	S	N	N/A	N/A	N/A	N/A	0.32	0.89	34
Walnut	S	N	S	N	N/A	N/A	N/A	N/A	-	-	-
Honey Walnut	S	N	S	N	N/A	N/A	N/A	N/A	-	-	-
Rosewood	S	N	S	N	N/A	N/A	N/A	N/A	-	-	-
Ashwood	S	N	N	N	N/A	N/A	N/A	N/A	-	-	-

Testing results for Kynar 500® or Hylar 5000® PVDF Resin-Based Color Finishes coil coating applications:

- Specular Gloss: (ASTM D-523) Low and medium gloss only
- Color Uniformity: (ASTM D-2244) Color controlled both instrumentally and visually
- Dry Film Thickness: (ASTM D-7091, ASTM D-1005, NCCA 11-13, 11-14, 11-15) Primer 0.20 ± 0.05 mil, topcoat 0.75 ± 0.05 mil
- Hardness: (ASTM D-3363, NCCA 11-12, Eagle Turquoise Pencils) HB Minimum
- Adhesion (X-Cut): (ASTM D-3359) No adhesion loss
- Adhesion (Crosshatch): (ASTM D-3359) No adhesion loss
- Abrasion Coefficient: (ASTM D-968) 100 liters/mil topcoat
- Direct Impact Flexibility: (ASTM D-2794, Gardner Impact Tester, 1/10" Distortion) Excellent, no removal
- Reverse Impact Flexibility: (NCCA Spec. 11, ASTM D-2794, Gardner Impact Tester, 5/8" ball Impact force in inch pounds equal to metal thickness) Excellent, no cracking or loss of adhesion
- Formability: (ASTM D-4145, 180° T-Bend on 1/8 Mandrel) No cracks or loss of adhesion
- Erosion: (20 years, 45° South Florida) Maximum 15% loss
- Humidity Resistance: (ASTM D-2247) Passes 2000 hours on Galvalume® and 4000 hours on Aluminum
- Acid Resistance: (ASTM D-1308, Proc. 3.1.1, 10% Sulfuric Acid spot test, 24 hour exposure) Excellent, no effect
- Salt Spray Resistance: (ASTM B-117) Passes 2000 hours on Galvalume® and 4000 hours on Aluminum
- Alkali Resistance: (ASTM D-1308, Proc. 5.2, 10% Sodium Hydroxide, 24 hour exposure) Excellent, no effect
- Detergent Resistance: (ASTM D-2248, 72 hours immersion in 3% solution at 100°F) Excellent, no effect
- Resistance to Acid Pollutants: (ASTM D 1308 Proc. 3.1.1, 24 hour exposure 10% HNO₃ vapors) Excellent, no effect
- Weathering - Color Retention: (ASTM D-2244, 20 years, 45° South Florida) Maximum 5 NBS units color change
- Weathering - Chalk Resistance: (ASTM D-4214, 20 years, 45° South Florida) Not worse than No. 8 rating

Notes:

1. ASTM - American Society for Testing Materials
2. NCCA - National Coil Coating Association
3. Galvalume® is 55% Aluminum-Zinc alloy coated sheet steel and is a registered trademark of BIEC International Inc.
4. Kynar 500® is a registered trademark belonging to Arkema, Inc.
5. Hylar 5000® is a registered trademark belonging to Solvay Solexis, Inc.

S Stock Color; Not subject to a minimum order
 N Non-Stock Color; subject to inventory on hand; 4,500 sf minimum order for 22 Gauge and 0.032 & 0.040 Aluminum
 N/A Not Available
 * Consult BMC on product availability. Premium and Metallic finishes are subject to a nominal surcharge, contact BMC for additional information.
 ** Consult Berridge on pricing and availability for Print Pattern Finishes.

BMC SAN ANTONIO
 6515 Fratt Rd.
 San Antonio, TX 78218
 (210) 650-3050
 Fax (210) 650-0379

BMC HOUSTON
 1720 Maury St.
 Houston, TX 77026
 (713) 223-4971
 Fax (210) 650-0379

BMC DALLAS
 2015 California Crossing
 Dallas, TX 75220
 (972) 506-8496
 Fax (210) 650-0379

BMC DENVER
 7505 E. 41st Ave.
 Denver, CO 80216
 (303) 322-3703
 Fax (210) 650-0379

BMC CHICAGO
 1175 Carolina Dr.
 W. Chicago, IL 60185
 (630) 231-7495
 Fax (210) 650-0379

BERRIDGE FLORIDA SALES CORPORATION***
 8802 Venture Cove
 Tampa, FL 33637
 (813) 335-4505
 Fax (210) 650-0379

BMC PHOENIX
 5717 W. Washington St.
 Phoenix, AZ 85043
 (602) 385-1237
 Fax (210) 650-0379

BMC ATLANTA
 319 Lee Industrial Blvd.
 Austell, GA 30168
 (770) 941-5141
 Fax (210) 650-0379

BMC OKLAHOMA CITY
 1400 Exchange Ave.
 Oklahoma City, OK 73108
 (405) 248-7404
 Fax (210) 650-0379

BMC KANSAS CITY
 1235 Southwest Blvd.
 Kansas City, KS 66103
 (913) 227-0855
 Fax (210) 650-0379

BERRIDGE CALIFORNIA SALES CORPORATION***
 8442 Sultana Ave.
 Fontana, CA 92335
 (562) 402-2081
 Fax (210) 650-0379

*** Berridge California and Florida Sales Corporations are separate entities from Berridge Manufacturing Company.



CORPORATE & SALES HEADQUARTERS
 2610 Harry Wurzbach Road
 San Antonio, TX 78209
 (210) 650-3050
 Fax (210) 650-0379

MANUFACTURING FACILITY
 2201 Rudeloff Road
 Seguin, TX 78155
 (830) 401-5200
 Fax (210) 650-0379

WWW.BERRIDGE.COM